

TECH DATA VULTREX™ MPG & G-124 PREMIUM HEAVY DUTY GREASE

INTRODUCTION

Petro-Canada Lubricant's VULTREX MPG and G-124 family of greases are premium performance, high dropping point, extreme pressure (EP), aluminum complex greases designed for a wide variety of heavy duty applications. The VULTREX MPG and G-124 grease family consists of different products formulated to meet a wide range of temperature conditions, load carrying capabilities and pumpability requirements. The aluminum complex thickener provides excellent resistance to water wash-off, while high oil viscosities and performance additives provide excellent film strength and metal protection. The VULTREX MPG and G-124 family of greases are recommended for heavy duty applications, such as:

- Construction equipment
- Farm machinery
- Mining and mineral processing
- Industrial machinery
- Forestry operations

FEATURES AND BENEFITS

Heavy duty wear protection

- Maintains a constant lubricating film under high load conditions which prevents wear
- Protects against severe shock loads

Year-round performance

 Oil viscosities and thickener adjusted for different temperature ranges from the hottest summer to the coldest winter conditions

Excellent high temperature stability

- Keeps its structure and consistency without hardening like some other greases
- Can be heated and cooled without causing separation of oil and thickener

Outstanding adhesive properties

 Withstands being squeezed out from between metal surfaces and resists throw off

APPLICATIONS

The VULTREX MPG and G-124 family of aluminum complex greases are characterized by their outstanding ability to withstand high pressures, shock loads and water washoff as well as operate over a wide range of temperatures. Consequently, VULTREX MPG and G-124 greases are recommended for use in a wide range of applications that include mining, mineral processing, forestry, steel mills, construction and farming operations. The VULTREX G-124 grease is designed specially for lubricating truck components and other heavy duty automotive equipment.

VULTREX MPG Synthetic Arctic and EP1 meet the P & H 472 specification for multipurpose greases, and are on the Certified Lubricant Listing for the Bucyrus International SD4711 multi-purpose grease specification.

VULTREX MPG EP 1

VULTREX MPG EP 1 is a grease that is recommended for lubricating heavily loaded plain or anti-friction bearings as well as sliding surfaces moving at low to moderate speeds. It is suitable for use with centralized lubrication systems. Specific applications include:

- Off-highway vehicle chassis and wheel bearings
- Ball mill conveyor and crusher bearings
- Low-medium speed gear couplings
- Steel mills, especially for bearings on slab casters
- Operating range is -25°C to 160°C (-13°F to 320°F)

VULTREX MPG Synthetic Arctic

VULTREX MPG Synthetic Arctic is a synthetic grease designed for use in extremely cold weather on resource industry equipment such as shovels, draglines, excavators, blasthole drills, tracked equipment and other slow moving vehicles. This synthetic grease is compatible with the other grades of VULTREX MPG grease. An NLGI No. 0 consistency and a lower viscosity synthetic fluid allows the grease to be pumped down to -45°C. It is suitable for use in centralized greasing systems. Operating range is -45°C to 120°C (-49°F to 248°F).

VULTREX G-124

VULTREX G-124 (NLGI No.2) is a red, tacky grease designed specially to lubricate heavy duty truck components such as wheel bearings, bushings, king pins, chassis points, etc. encountered in the mining, forestry and transportation industries. These applications involve vibration and shock loading which require EP properties. Operating range is -20°C to 160°C (-4°F to 320°F).

TYPICAL PERFORMANCE DATA

| Property | Test Method | VULTREX | | |
|---|-------------|----------------------------|----------------------------|---------------------------|
| | | MPG EP1 | MPG Synthetic Arctic | G-124 |
| NLGI Grade | D217 | 1 | 0 | 2 |
| Colour | PCM 264 | Brown | Brown | Red |
| Texture | PCM 264 | Buttery | Buttery | Stringy |
| Dropping Point, °C | D2265 | 247 | 244 | 277 |
| Worked Penetration 60 strokes | D217 A | 333 | 366 | 279 |
| Oxidation Stability 100 hrs, psi drop | D942 | 7 | 3 | 1 |
| Base Oil Viscosity cSt @ 40°C SUS @ 100°F | D445 | 473 2550 | 151 775 | 220 1168 |
| Four Ball Weld Point, kg | D2596 | 400 | 400 | 315 |
| Four Ball Wear, scar diam mm | D2266 | 0.4 | 0.6 | 0.5 |
| Copper Corrosion | D4048 | 1b | 1b | 1a |
| Water Washout % @ 79°C | D1264 | 8.6 | 10.8 | 2.5 |
| Normal Operating Temperature Range, °C (°F) | | -25 to 160 (-13 to 320) | -45 to 120 (-49 to 248) | -20 to 160 (-4 to 320) |

The values quoted above are typical of normal production. They do not constitute a specification.

Learn more about us: lubricants.petro-canada.com

Contact us: lubecsr@hfsinclair.com

Committed to the disciplined operation of our business.



Petro-Canada Lubricants Inc.

2310 Lakeshore Road W. Mississauga, Ontario, Canada L5J 1K2 **lubricants.petro-canada.com**